

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01D 53/64, 53/28, B01J 20/06, 20/04	A1	(11) International Publication Number: WO 99/22848 (43) International Publication Date: 14 May 1999 (14.05.99)
(21) International Application Number: PCT/US98/18846 (22) International Filing Date: 10 September 1998 (10.09.98) (30) Priority Data: 08/964,934 5 November 1997 (05.11.97) US (71) Applicant: MILLIPORE CORPORATION [US/US]; 80 Ashby Road, Bedford, MA 01730 (US). (72) Inventor: SNOW, James, T.; 55 Parrish Hill Drive, Nashua, NH 03063 (US). (74) Agents: HUBBARD, John, Dana et al.; Millipore Corporation, 80 Ashby Road, Bedford, MA 01730 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS AND APPARATUS FOR REMOVING METAL CARBONYLS AND MOISTURE FROM A GAS (57) Abstract A process and composition for removing metal carbonyls and moisture from a gas wherein the gas is contacted with a metal oxide, an organometallic oxide or mixtures thereof having a reduction potential greater than about 0.175 volts and a composition capable of removing moisture from the gas.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PROCESS AND APPARATUS FOR REMOVING METAL CARBONYLS AND MOISTURE FROM A GAS

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a process and apparatus for removing a metal carbonyl composition and moisture from a gas. More particularly, this invention relates to a process and apparatus for removing from a gas a metal carbonyl composition and moisture present in a gas to be treated, as well as moisture formed during removal of metal carbonyl composition from the gas.

2. Description of Prior Art

At the present time, numerous industries require the use of purified gases in their processes. Even parts per million (ppm) or parts per billion (ppb) levels of contaminants can have deleterious effects on the appearance or performance of certain products. The 1994 Semiconductor Industry Association (SIA) recommendation for semiconductor processing established key impurity level specifications in bulk and specialty gases for 0.25 μm processing of 0.1 - 1.0 and 1 - 100 ppb, respectively. The individual metal on silicon wafer specification for the same device geometry was set at 2.5×10^{10} atoms/cm². Because of these requirements and other observed adverse effects of using unpurified gases, the purification of process and purge gases in the microelectronics industry has found widespread acceptance and usage. The ideal purification material would remove the unwanted impurities without generating volatile by-products that would contaminate the gas. Also, the purification material should not be volatile under vacuum or pressurized process flow conditions. It would additionally be desirable for the purification material to chemically convert any toxic impurities into less toxic,

nonvolatile by-products. Ideally, the purification material would operate at room temperature and not require electrical power for operation.


Lindley, et al *Solid State Technol.* **1997**, 40 (8), 93 describes the enhanced selectivity for dielectric etch when CO is incorporated in the etch chemistry. This selectivity is required for production of semiconductor devices with geometries $\leq 0.35 \mu\text{m}$. Unfortunately, the reaction of CO with certain metals, e.g., iron and nickel, is thermodynamically favored to form volatile metal carbonyls that can deposit on the wafer resulting in undesired metal contamination. This was observed in Cooper, G. *Semiconductor Intl.* **1997**, 20 (8), 301 that describes experimental results showing increased levels of metals, e.g., iron, chromium and nickel, contamination on silicon wafers when CO is packaged in steel vs. aluminum gas cylinders. However, there was still observed an increase in nickel contamination using the aluminum cylinder versus the unetched control silicon wafers that was thought to be due to reaction of CO with the nickel in the Hastelloy tubing and nickel gaskets used in the study. Xu, et al *J. Mol. Catal.* **1993**, 83, 391 describe the ready formation of iron pentacarbonyl, $\text{Fe}(\text{CO})_5$, from the reaction of CO and the stainless steel surface of a FTIR cell. In addition, both $\text{Fe}(\text{CO})_5$ and nickel tetracarbonyl ($\text{Ni}(\text{CO})_4$) are very toxic with Threshold Limit values (TLV) of 100 and 50 ppb, respectively.

Golden, et al *Ind. Eng. Chem. Res.* **1991**, 30 (3), 502 describe the adsorption of trace levels of $\text{Fe}(\text{CO})_5$ and $\text{Ni}(\text{CO})_4$ using five commercially available adsorbents, i.e., activated carbon, silica gel, activated alumina, a methanol catalyst and HY zeolite. The activated carbon and zeolite showed the largest adsorption capacities for the carbonyls and were further investigated for carbonyl desorption at elevated temperatures. The desorption of $\text{Fe}(\text{CO})_5$ was observed from the zeolite and only a slight amount ($<0.1\%$) from the carbon; however, $\text{Ni}(\text{CO})_4$ was completely desorbed from the carbon at elevated temperatures. In addition, the presence of other impurities, e.g.,

carbon dioxide (CO₂), in the gas was shown to reduce the adsorption capacity of the adsorbents towards the metal carbonyls. The removal of these metal carbonyls via physisorptive processes with the concomitant concentration of these toxic impurities within a purifier will result in a safety and health hazard when the time comes to replace the purifier.

U.S. Patent No. 4,608,239 describes a process for removing Fe(CO)₅ from CO containing gases using a scavenger consisting of an alkali metal hydroxide in conjunction with a high boiling hydroxylic solvent. The use of solvents is undesirable because the vapors from these solvents will contaminate the downstream products with carbon and oxygen impurities under vacuum or pressurized flow conditions.

International Patent Application Publication No. WO 94/25142 describes a scavenger of lead oxide, PbO, dispersed upon a support to remove metal carbonyls from a gas. In this application there is some uncertainty as to whether the carbonyls are removed by chemical or physical means. However, from the data, it may be simply by physisorption since black deposits were only observed when the temperatures were >100°C, i.e., decomposition of the carbonyl. Irreversible removal of the toxic carbonyls by chemisorption is desired from a safety standpoint. While PbO has sufficient reduction potential to oxidize iron and nickel carbonyls to their respective salts, the PbO will concomitantly be reduced to lead metal with the generation of moisture impurity as shown below in the case of Fe(CO)₅:



The hydrogen ion is commonly found present in support materials and gases as a contaminant. The release of moisture impurity into the purified gas stream is not desirable since moisture can have deleterious effects in certain manufacturing processes, e.g., semiconductor manufacturing.

Czech. Patent No. CS 187947 B describes a scavenger for $\text{Fe}(\text{CO})_5$ and sulfur compounds from gas mixtures consisting of a catalyst having as its principal components, Cu and/or CuO and ZnO. These scavengers have the same undesirable characteristics, i.e., release of moisture impurity, as do the scavengers described in International Patent Application No. WO 94/25142.

U.S. Patent No. 4,853,148 describes scavengers for removing water impurity consisting in one case of a metal halide compound dispersed in a support having formula MX_y , where M is a y-valent metal selected from the group consisting of lithium (I), beryllium (II), magnesium (II), calcium (II), strontium (II), barium (II), cadmium (II), nickel (II), iron (II), iron (III), zinc (II), and aluminum (III); and y is an integer whose value is from one to three. This scavenger has the advantage over other adsorbents, e.g., zeolites and alumina, in that there is no competition for adsorption of moisture with the gas to be purified or other gas impurities, e.g., CO_2 . The scavenger disclosed by this patent is only capable of removing moisture and not other impurities, e.g., metal carbonyls and sulfur compounds.

It would be desirable to provide a composition suitable for removal of volatile metal carbonyls either alone or together with other impurities such as sulfur compounds from a gas while avoiding release of moisture into the gas. It would additionally be desirable to reduce the moisture concentration of the gas. It would also be desirable that such removal is accomplished by chemisorption and not physisorption mechanisms to prevent reversible release of the sorbed composition. Furthermore, it would be desirable to provide such a composition which is effective for use at normal operating pressure and room temperature.

SUMMARY OF THE INVENTION

The present invention provides a process and apparatus for removing metal carbonyls from a feed gas while avoiding the release of moisture into the gas. In addition, the present invention provides

such a process and apparatus which also removes moisture present in the initial feed gas. The apparatus of this invention comprises a housing containing a particulate composition which is an active scavenger for removing metal carbonyls and moisture from a gas. The housing includes an inlet for a feed gas and an outlet for treated gas. The particulate composition is formed of a mixture of particles comprising particles formed from a support coated with a scavenger for metal carbonyls and/or particles of a metal carbonyl scavenger as well as particles formed from a support coated with a scavenger for moisture and/or particles of a moisture scavenger.

Metal carbonyl removal from gas is effected by passing the gas through a bed of the particles under conditions to effect oxidation of the metal carbonyl and release of carbon monoxide derived from the metal carbonyl. Any moisture formed during the oxidation, such as when hydrogen ion is present in the gas or in the apparatus for treating the gas, is retained by the moisture scavenger.

Since hydrogen ion is normally present in most gases, it will readily react even in low concentrations with oxygen atoms produced during the oxidation reaction to form moisture. Thus, the moisture scavenger is positioned either downstream of the scavenger for metal carbonyl or in admixture with the scavenger for metal carbonyls in order to remove moisture formed during the oxidation reaction.

BRIEF DESCRIPTION OF THE FIGURES

Fig. 1 is a schematic drawing of an apparatus of this invention.

Fig. 2 shows the absorption spectra of CO gas containing nickel carbonyl and of purified CO gas free of nickel carbonyl produced in accordance with this invention.

Fig. 3 shows the difference in absorption spectra of CO gas treated to remove iron carbonyl and moisture in accordance with this invention vs. the prior art.

DESCRIPTION OF SPECIFIC EMBODIMENTS

In accordance with the process of this invention, a gas containing a metal carbonyl is contacted with a mixture of particles which include a scavenger for a metal carbonyl and a scavenger for moisture or sequentially with a scavenger for a metal carbonyl followed by contact with a scavenger for moisture.

The scavengers for metal carbonyls according to the present invention consist of:

- a) an active scavenger having a reduction potential greater than about 0.175 volts comprising a metal oxide, organometallic oxide or mixtures thereof;
- b) an active scavenger for removing moisture from the gas passing through the apparatus of this invention; and
- c) a high surface area support material that can consist of either (a) and/or (b).

The oxidizing reagents are selected such that the reduction potential is sufficient to effect oxidation of the metal carbonyl compounds. Representative suitable metal oxides include oxides of manganese, chromium, copper, silver, iron, vanadium, titanium, antimony, bismuth, lead, and mixtures thereof or the like. Representative organometallic oxides include species such as pyridinium chlorochromate (PCC), pyridinium dichromate, and chromium (VI) oxide-3,5-dimethoxypyrazole complex or the like. These scavengers also are useful for removing sulfur containing species including H_2S , SO_2 and CH_3SH . The preferred scavengers for metal carbonyls are CuO , Fe_2O_3 , MnO_2 or $\text{C}_5\text{H}_6\text{ClCrNO}_3$ (PCC).

The moisture removal capacity or efficiency of the active scavenger for removing moisture is not affected by the presence of

other impurities that would preferentially compete with moisture for binding to the support. The active scavenger for removal of moisture impurity either present in the feed gas or generated as a by-product from the reaction of the metal oxide or organometallic oxide species with the metal carbonyl impurity includes species such as anhydrous magnesium halide species on a support.

The active moisture absorber can be:

(i) metal halide compounds dispersed in the support, of the formula MX_y ;

(ii) metal halide pendant functional groups, of the formula $-MX_{y-1}$, covalently bonded to the support, wherein

M is a y-valent metal selected from the group consisting of lithium (I), beryllium (II), magnesium (II), calcium (II), strontium (II), barium (II), cadmium (II), nickel (I), iron (II), iron (III), zinc (II), and aluminum (III) and mixtures thereof;

y is an integer whose value is from 1 to 3; and

the activating scavenging moiety metal halide compounds and/or metal halide pendant functional groups have been formed by reaction of corresponding partially or fully alkylated compounds and/or pendant functional groups, with the gaseous hydrogen halide, to form the active scavenging moiety metal halide compounds and/or metal halide pendant functional groups;

the vapor pressure of the support is less than 1 ppm;

M is selected such that the heat of formation of its hydrated halide, $Mx_y \cdot (H_2O)_n$ is greater than or equal to 10.1 kilocalories per mole of such hydrated halide compound for each hydrated water molecule, wherein n is the number of water molecules bound to the metal halide in the metal halide hydrate as disclosed in U.S. Patent 4,853,148 which is incorporated herein by reference. Representative alternative

moisture scavengers which can be utilized include scavengers such as BaO, MgSO₄, CaCl₂, CaSO₄, or the like.

When not employing particles consisting of the metal carbonyl scavenger or the moisture scavenger, a support for the metal carbonyl scavenger or moisture scavenger can be utilized to form the particles.

Suitable support materials according to this invention include any materials that are compatible with the fluid being purified and any by-products produced during the purification reactions. They typically have the characteristics of:

- a) high surface area, generally greater than 50 m²/g;
- b) high porosity; and
- c) good thermal stability.

Representative support materials include alumina, silica, carbon, titania, magnesia, zeolites, and highly crosslinked polymers. The preferred support material is alumina.

The active chemistries utilized in the scavengers of this invention may be deposited on the same or different high surface area support materials. The support material itself may function as one of the active chemistries. In the case of utilizing different support materials for the active chemistries, the separate materials can exist within the purification vessel as a homogeneous mixture or layered beds.

Representative gases which are purified by removing metal carbonyls and moisture impurities include carbon monoxide and inert gases such as argon, helium, nitrogen or the like. Any other gases can be treated provided they are compatible with the described scavengers.

Fig. 1 illustrates the use of the present invention. Referring to Fig. 1, an apparatus of this invention 10 includes an inlet 12, an outlet 14 and a housing 16. Particles 18 can comprise a mixture of metal carbonyl scavenger particles and moisture scavenger particles. Alternatively, the metal carbonyl scavenger particles can be positioned

adjacent the inlet 12 while the moisture scavenger particles are separately positioned adjacent the outlet 14. In a third alternative, the metal carbonyl scavenger particles can be positioned in a separate housing in an upstream position while the moisture scavenger particles can be positioned in a separate housing downstream of the housing for the metal carbonyl scavenger particles.

The following examples illustrate the present invention and are not intended to limit the same.

EXAMPLE 1

A chromium (VI) oxide on alumina support is prepared according to the following procedure: To a slurry of aluminum oxide (50.0 g) in deionized water (50 mL) is added with overhead mechanical stirring a solution of chromium (VI) oxide (12.0 g) in deionized water (25 mL). The resulting mixture is stirred for one hour, transferred to a round-bottomed flask and concentrated on a rotary evaporator. Additional drying is done at 120°C under vacuum for four hours.

EXAMPLE 2

A pyridinium chlorochromate on zeolite support is prepared according to the following procedure: To 2 N HCl solution (66 mL) is added at room temperature chromium (VI) oxide (12.0 g) with magnetic stirring. Pyridine (9.2 g) is added dropwise with stirring over ten minutes. The resulting solution is stirred for 15 minutes. NaY zeolite (50.1 g) is added to the solution resulting in a temperature increase of the mixture. The resulting mixture is allowed to stand for 1.5 h, then the mixture is filtered providing orange-colored zeolite. Drying of the PCC/NaY mixture is effected at 130°C under vacuum for four hours.

EXAMPLE 3

A commercially available copper oxide on alumina scavenger is dried according to the following procedure: A sample of CU-0226 S (50

cc) from Engelhard Corporation contained within a 50-cc stainless steel sample cylinder using metal frits inserted into the compression fittings is dried at 100°C and 3 slpm flow of purified nitrogen for 16 hours.

EXAMPLE 4

A mixture of copper oxide on alumina and anhydrous magnesium halide on alumina is prepared according to the following procedure: Within a nitrogen-filled glove box a sample of CU-0226 S (ca. 4 cc) prepared in Example 3 is used to partially fill a small sample vessel constructed from a 2.5 inch section of ½-inch OD stainless steel tubing, compression fittings, metal frits in the fitting to contain the scavenger and valves. To this scavenger is added anhydrous magnesium chloride on alumina scavenger (ca. 0.5 cc; Millipore Waferpure® Reactive Micro Matrix for chloride and oxide gases).

EXAMPLE 5

This example demonstrates the use of the chromium (VI) oxide on alumina scavenger for the removal of hydrogen sulfide (H₂S) from an inert gas stream. A 4.5-cc sample tube is filled with the CrO₃/alumina scavenger prepared in Example 1. A test gas mixture of 950 ppm H₂S in helium is passed through the sample tube initially at a flow rate of 375 sccm which is later increased to 750 sccm. The downstream H₂S concentration is measured using a residual gas analyzer (RGA). After consuming 146.25 L of challenge gas, H₂S breakthrough is detected by the RGA to provide a H₂S capacity for the inorganic scavenger of 31 L H₂S/L bed.

EXAMPLE 6

This example demonstrates the use of the pyridinium chlorochromate (PCC) on NaY zeolite scavenger for the removal of Ni(CO)₄ from carbon monoxide.

A 50-cc sample cylinder is filled with PCC/NaY zeolite sample prepared in Example 2. The sample cylinder is installed on a gas manifold with an optional by-pass loop around the sample. An unknown concentration of $\text{Ni}(\text{CO})_4$ is generated by heating a nickel filter in carbon monoxide to 130°C to provide the challenge gas mixture. This test gas mixture is either passed through the sample cylinder or optionally by-passed (to provide background level) at a flow rate of 48 sccm. The downstream by-passed and purified CO gas is measured using a FTIR and RGA.

Table 1 shows the observed results with values given in amps and ND is the abbreviation for none detected.

Table 1

	$^{60}\text{Ni}(\text{CO})_4$	$^{58}\text{Ni}(\text{CO})_4$	$^{60}\text{Ni}(\text{CO})_3$	$^{58}\text{Ni}(\text{CO})_3$	$^{60}\text{Ni}(\text{CO})_2$	$^{58}\text{Ni}(\text{CO})_2$
m/e	171	169	143	141	115	113
By-passed	0.20E-12	0.52E-12	0.56E-12	1.47E-12	0.35E-12	0.83E-12
Purified	ND	ND	ND	ND	ND	ND

The overlaid FTIR spectra of by-passed vs. purified CO gas is shown in Fig. 2. As shown in Fig. 2, the purified CO is free of $\text{Ni}(\text{CO})_4$ as shown in the dotted trace.

EXAMPLE 7

This example demonstrates the difference in downstream moisture impurity level through the use of anhydrous magnesium halide on alumina scavenger with the copper oxide on alumina scavenger in the removal of $\text{Fe}(\text{CO})_5$ vs. solely using the copper oxide on alumina scavenger. A 4.5-cc sample tube is filled with copper oxide on the alumina scavenger prepared in Example 3. A sample of $\text{Fe}(\text{CO})_5$ is contained in a small section of tubing with valve that is connected to a tee on a manifold upstream of the scavenger sample. The scavenger sample tube is installed on the manifold with an

optional by-pass loop around the sample. A ppm-level concentration of $\text{Fe}(\text{CO})_5$ in helium is generated by opening the valve to the diffusion tube containing the $\text{Fe}(\text{CO})_5$ to provide the challenge gas mixture. This test gas mixture is either passed through the sample cylinder or optionally by-passed (to provide background level) at a flow rate of 100 sccm. The downstream by-passed and purified CO gas is measured using a FTIR. Following this test a 4.5-cc sample tube containing a mixture of copper oxide on alumina and anhydrous magnesium chloride on alumina prepared in Example 4 is tested in a similar fashion on the manifold. The difference in FTIR spectra is shown in Figure 3. As shown in Fig. 3, the spectrum for the scavenger containing only copper oxide on alumina (the upper spectrum) shows many absorbencies corresponding to the presence of moisture. However, for the spectrum of the mixed purifier containing copper oxide and active moisture scavenger (magnesium halide), the moisture level is near the detection limit of the instrument. This result demonstrates the improved performance of utilizing an active moisture scavenger which forms hydrates upon reaction with moisture as compared to physisorptive dessicants.

CLAIMS

1. A particulate composition suitable for removing a metal carbonyl composition and moisture from a gas, as well as for removing a moisture by-product formed during removal of said carbonyl composition from said gas which comprises:

a particulate mixture comprising first particles including a surface formed of a first composition having a reduction potential greater than about 0.175 volts selected from the group consisting of a metal oxide, an organometallic oxide and mixtures thereof and second particles including a surface formed of a second composition capable of removing moisture from said gas.

2. The composition of claim 1 wherein said first composition is a metal oxide.

3. The composition of claim 1 wherein said first composition is an organometallic oxide.

4. The composition of claim 2 wherein said metal oxide is CuO.

5. The composition of any one of claims 1, 2, 3 or 4 wherein said second composition is a metal halide of the formula MX_y , wherein M is a y-valent metal selected from the group consisting of lithium, beryllium, magnesium, calcium, strontium, barium, cadmium, iron, zinc, aluminum and mixtures thereof and y is an integer from 1 to 3.

6. The process for removing metal carbonyls and moisture from a gas, including moisture formed as a result of removal of metal carbonyls from said gas, which comprises intimately contacting said gas with the composition of claim 1 and recovering said gas after contacting with composition of claim 1.

7. The process of claim 6 wherein said first composition is a metal oxide.
8. The process of claim 6 wherein said first composition is an organometallic oxide.
9. The process of claim 7 wherein the metal oxide is CuO.
10. The process of claims 6, 7, 8 or 9 wherein said second composition is a metal halide of the formula MX_y , wherein M is a y-valent metal selected from the group consisting of lithium, beryllium, magnesium, calcium, strontium, barium, cadmium, iron, zinc, aluminum and mixtures thereof and y is an integer from 1 to 3.
11. The process for removing metal carbonyls from a gas which comprises contacting said gas sequentially with a first particulate composition having a reduction potential greater than about 0.175 volts selected from the group consisting of a metal oxide, an organometallic oxide and mixtures thereof and then with a second particulate composition having a surface composition capable of removing moisture from said gas.
12. The process of claim 11 wherein said first composition is a metal oxide.
13. The process of claim 11 wherein said first composition is an organometallic oxide.
14. The process of claim 12 wherein the metal oxide is CuO.
15. The process of claims 11, 12, 13 or 14 wherein said second composition is a metal halide of the formula MX_y , wherein M is a

15

y-valent metal selected from the group consisting of lithium, beryllium, magnesium, calcium, strontium, barium, cadmium, iron, zinc, aluminum and mixtures thereof and y is an integer from 1 to 3.

1/3




Figure 1

2/3




Figure 2

3/3




Figure 3

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/18846

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B01D53/64 B01D53/28 B01J20/06 B01J20/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01D B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	FR 2 040 232 A (MONSANTO CO) 22 January 1971 see page 4, line 33 - line 35; claims 1-3 ---	1,2,4-7, 9-12,14, 15
Y	US 4 853 148 A (TOM GLENN M ET AL) 1 August 1989 cited in the application see abstract --- -/--	1,2,4-7, 9-12,14, 15

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 January 1999

Date of mailing of the international search report

18/01/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Faria, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/18846

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 96, no. 20, 17 May 1982 Columbus, Ohio, US; abstract no. 164903, DVORAK ET AL: "Removing small residual quantities of sulfur compounds and/or iron pentacarbonyl from gas mixtures" page 131; XP002089216 cited in the application see abstract & CS 187 947 B (DVORAK LADISLAV) 28 February 1979 ---	1,2,4,6, 7,9,11, 12,14
A	US 4 740 361 A (HEYD ROBERT L ET AL) 26 April 1988 see claims 1,3 ---	1,2,6,7, 11,12
A	PATENT ABSTRACTS OF JAPAN vol. 097, no. 002, 28 February 1997 & JP 08 281063 A (JAPAN PIONICS CO LTD), 29 October 1996 see abstract -----	1,2,4,6, 7,9,11, 12,14

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. l. Application No

PCT/US 98/18846

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2040232 A	22-01-1971	US 3624165 A	30-11-1971
US 4853148 A	01-08-1989	AT 106855 T	15-06-1994
		DE 3889953 D	14-07-1994
		DE 3889953 T	15-09-1994
		EP 0283965 A	28-09-1988
		ES 2056846 T	16-10-1994
		JP 2031606 C	19-03-1996
		JP 7061416 B	05-07-1995
		JP 63256120 A	24-10-1988
		US 5057242 A	15-10-1991
		US 4925646 A	15-05-1990
		US 5094830 A	10-03-1992
US 4740361 A	26-04-1988	CA 1266366 A	06-03-1990
		EP 0239111 A	30-09-1987
		JP 1801224 C	12-11-1993
		JP 5011487 B	15-02-1993
		JP 62277122 A	02-12-1987